

Gallagher Ltd

 James Corbett Road
 Salford
 Manchester
 M50 1DE

BS EN 12390-3 : 2009 Concrete Cube Test Certificate

certificate number 10004794	certificate date 10/09/2020
site James Corbett Road	test lab North West

cube ref customer 3	date cast 13/08/2020	test age (days) 28
cube ref MATtest 4794	date received 12/08/2020	date tested 10/09/2020
mix type NFSMR 50/50 Mix	slump	location Stockpile 7

<input checked="" type="checkbox"/> 100mm Cube	<input type="checkbox"/> 150mm Cube	Other Cube mm: 86.8
fail load (kn) 12.4	wt (water) (g) 0	mass (air) (g) 1505

BS EN 12390 Result (At age 28 days. Sampled on 13/08/2020)

compressive strength (N/mm²) 1.6	density (kg/m³) 1500
--	--

Remarks

1. Sampled by MATtest Midlands Limited
8. Damaged/missing corners

Other Comments

Made 1 day after sampling at request of Client. Made with Material which passes 20mm sieve at request of Client.

Sample was found to be too brittle to weigh in water, therefore nominal dimensions were used after checking and found to be appropriate.

Cured in the laboratory in accordance with BS EN 12390-2 : 2009 at 20°C +/-2°C unless otherwise stated

Tested in accordance with BS EN 12390-3 : 2009 unless otherwise stated

Density determined by water displacement in accordance with BS EN 12390-7 : 2009

Tested in a saturated condition unless otherwise noted


Type of failure normal unless otherwise noted



7806

details checked by:

J. Pullar - Technical Manager

signed


Reproduction or creating a hard copy of this document may result in distortion of the accreditation symbols.