

MATtest Laboratories  
Unit 5 Draycott Mills  
Off Market Street  
Draycott  
Derbyshire  
DE723NB

Date: 15 May 2020  
Test Report Ref: TR 731051

Page 1 of 1

Contract: James Corbet Road Depot, Eccles, Salford.

**LABORATORY TEST REPORT**

**TEST REQUIREMENTS:** To determine the Magnesium Sulfate Value of aggregate sample within the size range 10mm to 14mm in accordance with **BS EN 1367-2 : 2009**

**SAMPLE DETAILS:**

Certificate of sampling received:	Yes
Laboratory Ref. No:	<b>S87404</b>
Client Ref. No:	<b>A2683</b>
Date and Time of Sampling:	<b>18/03/2020</b>
Date of Receipt at Lab:	<b>20/04/2020</b>
Date of Start of Test:	<b>29/04/2020</b>
Sampling Location:	<b>Stockpile from Bay 7</b>
Name of Source:	<b>James Corbet Road Depot, Eccles, Salford</b>
Method of Sampling:	<b>Unknown</b>
Sampled By:	<b>Client</b>
Tested By:	<b>DW</b>
Material Description:	<b>NFSMR/50/50/Mix</b>
Target Specification:	<b>N/A</b>

**RESULTS:**

**Magnesium Sulfate Value Portion 1 ( $MS_1$ ) = 11.4**

**Magnesium Sulfate Value Portion 2 ( $MS_2$ ) = 12.7**

**Mean Magnesium Sulfate Value ( $MS$ ) = 12**

This test report shall not be reproduced, except in full, without the written approval of Celtest Company Limited.

These results relate only to the items tested.

**Comments**

**Proportion by mass of laboratory sample used for the test portion = 5% (nearest 5%)**

Report checked and approved by:



Mathew Sayer  
Aggregate Team Manager