

Gallagher Ltd

James Corbett Road
 Salford
 Manchester
 M50 1DE

BS EN 12390-3 : 2009 Concrete Cube Test Certificate


certificate number 10006288	certificate date 03/12/2020
site James Corbett Road	test lab North West


cube ref customer 3	date cast 05/11/2020	test age (days) 28
cube ref MATtest 6288	date received 04/11/2020	date tested 03/12/2020
mix type NFSMR 50/50 Mix	slump	location Stockpile 5 (Made 03/11/20)

<input checked="" type="checkbox"/> 100mm Cube	<input type="checkbox"/> 150mm Cube	Other Cube mm: 100.0
fail load (kn) 23.1	wt (water) (g) 0	mass (air) (g) 2082.7

BS EN 12390 Result (At age 28 days. Sampled on 05/11/2020)	
compressive strength (N/mm2) 2.3	density (kg/m3) 2080

Remarks	Other Comments
1. Sampled by MATtest Midlands Limited	Made 1 day after sampling at request of Client. Made with Material which passes 20mm sieve at request of Client. Sample was found to be too brittle to weigh in water, therefore nominal dimensions were used after checking and found to be appropriate.

<p>Cured in the laboratory in accordance with BS EN 12390-2 : 2009 at 20°C +/-2°C unless otherwise stated Tested in accordance with BS EN 12390-3 : 2009 unless otherwise stated Density determined by water displacement in accordance with BS EN 12390-7 : 2009 Tested in a saturated condition unless otherwise noted Type of failure normal unless otherwise noted</p>	 7806
--	---

details checked by:	J. Pullar - Technical Manager
<i>signed</i>	

Reproduction or creating a hard copy of this document may result in distortion of the accreditation symbols.